

We are IntechOpen, the world's leading publisher of Open Access books Built by scientists, for scientists

4,800

Open access books available

122,000

International authors and editors

135M

Downloads

Our authors are among the

154

Countries delivered to

TOP 1%

most cited scientists

12.2%

Contributors from top 500 universities



WEB OF SCIENCE™

Selection of our books indexed in the Book Citation Index
in Web of Science™ Core Collection (BKCI)

Interested in publishing with us?
Contact book.department@intechopen.com

Numbers displayed above are based on latest data collected.
For more information visit www.intechopen.com



Experimental Design and Response Surface Analysis as Available Tools for Statistical Modeling and Optimization of Electrodeposition Processes

Lilian F. Senna and Aderval S. Luna

*State University of Rio de Janeiro, Chemistry Institute,
Pavilhão Haroldo Lisboa da Cunha, Rio de Janeiro,
Brazil*

1. Introduction

Electrodeposition, also called electroplating, is one of the most commonly used methods for metal and metallic-alloy film preparation in many technological processes. This method is generally considered an economically interesting and easily controlled process to protect and enhance the functionality of parts used in diverse industries (home appliances, jewelry, automotive, aircraft/aerospace, and electronics) in both decorative and engineering applications. It promotes the appearance, extends the life, and improves the performance of materials and products in different media (Schwartz, 1994; Oriňáková et al., 2006).

Despite these applications, electrodeposition methods have, for decades, been industrially regarded as a means for the mass production of cheap materials and not for the production of advanced materials with high values. Their use has been limited to surface protection or plating of decorative metallic layers (Yoshida et al., 2009). The evolution of modern technology, however, has created increased demands on the structures and properties of deposits and directed the emphasis of electrodeposition mainly toward engineering processes and materials technology. Electrodeposition is now regarded as a state-of-the-art technology. For example, electrodeposited Cu is the material of choice for the interconnects in ultra-large-scale integrated (ULSI) circuits, and electrodeposited soft magnetic alloys are an important component of magnetic recording heads (Schwarzacher, 2004; Yoshida et al., 2009). In fact, the deposition of alloy coatings is one of the most rapidly expanding topics in the current literature (Oriňáková et al., 2006; Santana et al., 2006, 2007; Dubent, 2007; Ferreira et al., 2007; Silva et al., 2008; Brankovic et al., 2009; Gupta & Podlaha, 2010; Düzgün et al., 2010). Compared to the electrodeposition of a single metal, alloy coatings show better properties because their chemical composition can be varied to the required function. Alloy coatings are denser, harder, generally more resistant to corrosion, possess better magnetic properties and are suitable for subsequent coating by electrodeposition (Senna et al., 2003; Santana et al., 2006).

Nanostructured coatings, with their advanced properties, can also be produced by electrodeposition, where the nanoparticles are directly attached to the substrate.

Electrodeposition is considered a simple, fast, and inexpensive method and is among the most familiar binder-free techniques employed for the preparation of nanoparticles. In comparison to other techniques, the particle size, crystallographic orientation, mass, thickness, and morphology of the nanostructured materials can be controlled by adjusting the operating conditions and bath chemistry. These nanostructured coatings offer great potential for various applications because of their superior characteristics relative to those of conventional coatings (Mohanti, 2011; Lu & Tanaka, 1996; Huang. & Yang, 2005; Finot, et al., 1999; Gurrappa & Binder, 2008). In addition, recent research has been focused on demonstrating the feasibility of the co-deposition of ceramic materials with metals and polymers to create opportunities for the preparation of novel hybrid nanomaterials and nanostructures. Nanohybrid coatings result from the development of novel electrochemical strategies. These coatings exhibit advantageous properties compared with those of individual materials. The coatings also exhibit properties that cannot be obtained by other methods or with single-phase materials (Gurrappa & Binder, 2008; Tsai et al., 2010; Mosavat et al., 2011).

However, the production of the electrodeposited coatings, especially the alloys and hybrid coatings, is always a complex process. For each application, several critical parameters (chemical and operational) must be accurately controlled to fulfill the required characteristics of the produced coating. The conventional and classical methods of studying a deposition process are usually univariate methods in which most of the deposition parameters are maintained at constant values while one of them is varied in a chosen direction. The use of univariate methods means that, in practice, the best parameter values are often chosen empirically, and the coatings are then produced at “optimum conditions,” which may not represent the best conditions to obtain the desired coating properties (Ferreira et al., 2007). In addition, these experiments are time consuming, requiring a large number of experiments, and also produce substantial amounts of wastewater. Moreover, the influence of the combined parameters on the studied variables is not evaluated, which confirms that the optimum levels determined by these methods are generally unreliable (San Martín et al., 1998; Rabiote et al., 1998; Santana et al., 2007a, Santana et al., 2007b). Therefore, to ensure greater reproducibility and quality, the development of a more scientific approach that leads to a better understanding of alloy deposition phenomena is important.

One way to achieve a better approach, given the complexity of the deposition processes, is to use experimental design, response surface methodology, and other statistical techniques, in which all the parameters are varied simultaneously, showing the responses of their synergic and antagonistic interactions. These methodologies both drastically reduce the number experiments needed to optimize the process and give statistical inference on the optimum deposition conditions (Rabiote et al., 1998). These methodologies also allow improvements in both process performance and reliability, thereby decreasing the cost and the volume of produced wastewater in addition to leading to the creation of new coatings systems that can fulfill industrial needs (Ferreira et al., 2007; Santana et al., 2007a). Nevertheless, these tools are not extensively used to enhance the quality of the proposed electrodeposition baths or to achieve realistic optimized conditions, and the reports found in the literature are still related to few research groups. This work presents a review concerning the statistical approach for performing one or multi-responses experiments and

its application to the electrodeposition processes of metal and alloy coatings. Therefore, the main topics covered by this review will be the following:

- An overview of the electrodeposition process and the conventional methods used in the literature to perform a study concerning the production of metallic, alloy and hybrid coatings;
- A screening concerning factorial experimental designs and how these designs can be used in electrodeposition processes;
- The surface response method for one response variable or for multi-response variables;
- The optimization of the electrodeposition process using a statistical approach;
- The main results presented in the literature concerning the above-mentioned statistical topics applied to the electrodeposition of metal, hybrid, and alloy coatings.

2. Conventional and classic methods for the study and optimization of electroplating conditions

The production of coatings using electrodeposition was developed in the 1800s and is still considered a simple, low-cost and easy operational process. At a minimum, the electrodeposition of a single metallic coating requires an electrolyte containing the reducible metal ion, a conductive substrate, a counter electrode, a power supply, and a container to hold the electrolyte and electrodes. This simplicity accounts for the appeal of electrodeposition, but may also lead to some basic controls that are needed to ensure reproducibility being neglected (Jeerage & Schwartz, 2004). Different substrate preparations, stirring speeds, applied current densities (or potentials), and deposition temperatures, for example, are some parameters that must be well controlled to produce a coating with the desired qualities and to guarantee reproducibility. When an alloy or a hybrid coating is being produced, or even when a complexant agent or additives are included in the electrolytic bath, the complexity of the electrodeposition process increases, and the control of deposition parameters becomes more critical.

The literature contains several reports that propose electrolytic baths and electrodeposition processes for the production of different kinds of coatings for numerous applications. Figure 1 shows the main parameters that usually need to be controlled in an electrodeposition process. The kind of substrate used, the finish process used to prepare the substrate, the electrolyte composition (with respect to different ions and/or ion concentrations, additives, complexant agents, etc.), the physico-chemical characteristics of the solution (e.g., pH or conductivity), the mode of current used, and other parameters such as temperature or stirring speed can, together or individually, affect the quality and the properties of the produced electrodeposits. In general, most of the reports in the literature have involved the use of conventional univariate methods to study the influence of the deposition parameters on the deposition mechanisms and the coating properties. In these studies, each of the previously discussed parameters has been investigated separately while the others have been held at constant values. The best results obtained under the given conditions were then used to study the effects of another parameter, and so on. Few works include any kind of statistical evaluation, and those that do primarily present the average value and standard deviation. However, it is important to note that the obtained responses of the studied variables are valid only for the chosen experimental conditions. Examples from the literature can be found in later sections of this text.




Fig. 1. Main parameters usually controlled in an electrodeposition process.

2.1 Evaluation of the kind of substrate and/or the finish process in the electrodeposition process

Both the kind of substrate used and its finish process may cause differences in the electrodeposition process by influencing the morphology, the growth process, and other properties of the coatings. The substrate and finish process are particularly important when alloys and nanomaterials are produced or when a mechanism is developed. For example, Gomez & Vallés (1999) have noted that the initial stages of the electrodeposition of Co-Ni alloys were influenced by the kind of substrate used. The nucleation and three-dimensional growth, which resulted in compact, fine-grained and homogeneous deposition, occurred in all substrates, with preferential deposition of cobalt and anomalous co-deposition. Concerning the electrodeposition of Zn-Co alloys, Roventi et al. (2006) have observed no significant changes in the polarization curves and the composition of the coatings when the mild steel substrate was changed to platinum. On the contrary, when the substrate tested was glassy carbon, a strong decrease in current density was noted, which started to increase only when the electrode surface was completely covered by the alloy. This behavior was related to a strong inhibition of the deposition process on the glassy carbon cathode.

The properties of the substrate can also influence the coating characteristics. Kim et al. (2009) have shown that the substrate conductivity greatly affected the structural and optical properties of ZnO nanorods produced by cathodic electrodeposition: more conductive substrates favored the growth of high-quality ZnO nanorods at low temperature (80 °C). In addition, studying the effects of Zn substrate finish on the production of ZnO nanoplates, Illy et al. (2005) have observed that the as-received or mechanically polished Zn substrate was the most suitable substrate finish and allowed more highly aligned, dense structures to

be grown, whereas electropolished substrates formed inhomogeneous deposits. The investigations concerning this topic are generally performed by changing the substrate and/or its finish treatment while keeping all other parameters constant.

2.2 The effects of other deposition parameters on the coating properties

Because each system substrate/coating may exhibit a different behavior for each electrolyte used, the electrolyte composition, pH and (less often) conductivity are also important and typically studied parameters that can affect the electrodeposition process. Changes in the electrodeposition process occur if only one cation, several cations, or even dispersed particles are present in the electrolyte. Moreover, the solution pH and conductivity, as well as the presence of complexant agents and/or additives, are parameters considered when a new system is under investigation. Other parameters, such as current density, deposition potential, deposition temperature, and stirring speed are also studied. Several works may be used as examples to demonstrate the methodologies usually found in the literature to evaluate these parameters and attempt to find optimum conditions to produce the metallic/alloy/hybrid coatings.

The effects of additives and complexant agents on electrodeposition baths for deposition of metallic and alloy coatings has been investigated by a number of authors. For example, Healy & Pletcher (1998a, 1998b) have shown that the studied additives (Cl⁻, polyethylene glycol, and 4,5-dithiaoctane-1,8-disulfonic acid) adsorbed on the electrode at different deposition potentials and stirring speeds influences in the copper reduction mechanism. Similar results were observed by Bozzini et al. (2006) and Tantavichet & Pritzker (2006), who studied the effects of polyethylene glycol and benzotriazole, respectively. Nayana et al. (2011) have investigated the influence of additives on the morphology and brightness of nanocrystalline zinc electrodeposited from an acid sulfate bath. The mechanism of zinc deposition also changed in the presence of the additives. Drissi-Daoudi et al. (2003) have studied the influence of several complexant agents on the copper deposition mechanism and showed that the kind of complex formed (strong- or weak-field complex) affected the reduction potential of the metallic ion. The electrodeposition of Cu-Zn alloy on carbon steel from pyrophosphate-base baths in the presence of additives has been investigated by Senna et al. (2003) and Senna et al. (2005). The authors chose one stirring speed and pH value, whereas the bath composition and the current density were varied. Their results have shown that the alloy coating composition, the coating morphology, hardness and corrosion resistance were dependent on these two parameters. Coating compositions similar to that of bulk brass (70 % m/m Cu and 30 % m/m Zn) were obtained from baths that contained allyl alcohol as an additive.

The composition of the electrodeposition bath has been widely studied, in combination with the effects of pH, current density (or applied potential), temperature and stirring speed, as a means of controlling the coating composition and properties. Takata & Sumodjo (2007) have observed the effects of pH and the [Co²⁺]/[Pd²⁺] ratio on the composition, morphology and magnetic properties of electrodeposited Co-Pd thin films from a glycine bath. Initially, the pH was kept constant while the [Co²⁺]/[Pd²⁺] ratio was varied. As a result, the current efficiency was not affected, whereas the alloy composition changed, which resulted in an increase in the Pd content in the coating. Under these conditions, cracks were always observed, and increasing palladium content in the Co-Pd alloy resulted in deposits with

more cracks. The magnetic properties also changed with the increase in Pd content in the coating. Then, the authors maintained the bath composition and varied the pH between 6.5 and 9.4, which did not change the current efficiency or coating composition. All morphological and magnetic changes were related to other parameters (in this case, current density). While investigating the electrodeposition of hybrid coatings, Wu et al. (2004) have demonstrated the influence of the plating parameters on the electrodeposition of a Co-Ni- Al_2O_3 composite from a sulfamate electrolyte. Similar to the methods in previously discussed investigations, certain parameters were kept constant (such as the solution pH, deposition temperature, and current density) while others were varied separately (the cobalt concentration and the alumina concentration in the bath, for example). The authors were able to determine the best conditions to produce composite coatings with the maximum alumina content.

The current characteristics also affect the coating composition and morphology and need to be controlled to produce coatings with the desired properties. Vincenzo et al. (2010) have compared the tin deposition process from a commercial bath using direct and pulsed current. The authors noted several differences in the microstructure and in the properties of the coating after the application of pulsed current. Moreover, changes in the duty cycle and in the frequency of the pulsed current deposition mode also affected the cathodic efficiency and the coating microstructure. Ramanauskas et al. (2008) have studied the deposition of Zn-Ni, Zn-Co, and Zn-Fe alloys using pulsed current mode. The authors performed the electrodeposition experiments by varying one parameter at a time, with the other parameters being fixed at standard levels. The plating parameters studied included the peak cathodic current, i_p , the time of current on, t_{on} , and the time of current off, t_{off} . The coating compositions—mainly the zinc content in the studied alloy coatings—were strongly affected by these parameters. Topographic and phase changes were also noted. The best parameters for each alloy coating deposition were determined, and the coatings were produced on a steel substrate under their respective optimum conditions. The polarization curves of these coating/substrate systems were obtained in a naturally aerated NaCl + NaHCO_3 solution at pH = 6.8. The lowest i_{corr} values under all deposition conditions were exhibited by Zn-Ni coatings, whereas Zn-Co and Zn-Fe, except for t_{off} variation, exhibited similar corrosion resistance.

The previously discussed works and several other studies found in the literature produced valid and consistent results that can contribute to a better comprehension of the electrodeposition process and the mechanisms involved in the reduction of one or more ions in an aqueous bath. However, the use of univariate methods cannot allow the evaluation of simultaneous effects of more than one deposition parameter on the same variable. This limitation means that the joint effects of simultaneous variations in bath composition, current density, and temperature, for example, cannot be obtained by these methods. Consequently, the optimum conditions determined by variation of one of these parameters at time may not always represent the real process.

3. Optimization strategies and multivariate approach as a means for enhancing electrodeposition processes

Optimization strategies are procedures followed when, for instance, a product or a process is to be optimized. In an optimization, one tries to determine the optimal settings or conditions for a number of factors. Factors are parameters that can be set and reset at given

levels, e.g., temperature, pH, reagent concentrations, reaction time, etc., and that affect the responses of a product or process. The factors and their level ranges form the experimental domain within which the global optimum is sought. Factors also might “interact.” For instance, a two-factor interaction occurs when the influence of one factor on the response is different at different levels of the second factor.

When only one factor needs to be optimized, a simple univariate procedure is performed. Nonetheless, two or more factors are typically studied using either univariate or multivariate optimization strategies (Massart et al., 1997).

An applied univariate procedure, as previously discussed, is the one-variable-at-a-time (OVAT) approach, where only one factor at a time is varied and optimized. The OVAT procedure, however, has some disadvantages: interactions between factors are not taken into consideration; many experiments are needed when the number of factors increases; only a small part of the experimental domain is analyzed; the global optimum might not be found; and the found optimal conditions might depend on the starting conditions (Massart et al., 1997).

However, a multivariate approach varies several factors simultaneously. Multivariate approaches are subdivided into sequential and simultaneous procedures (Massart et al., 1997). Sequential procedures involve a few initial experiments and use their results to define the subsequent experiment (s) (Dejaegher & Vander Heyden, 2009). Sequential approaches can be applied when the experimental domain containing the optimum is *a priori* unknown, but are limited to the optimization of only one response. Simultaneous procedures perform a predefined number of experiments according to a well-defined experimental set-up, e.g., an experimental design (Massart et al., 1997).

An experimental design is an experimental setup to simultaneously evaluate numerous factors at given number of levels in a predefined number of experiments. Rigorously, experimental designs can be divided into screening designs and response surface designs. Screening designs involve screening a relatively large number of factors in a relatively small number of experiments. They are used to identify the factors with the strongest influence. Typically, the factors are evaluated at two levels in these designs. Response surface designs are used to find the optimal levels of the most important factors (which are sometimes selected from a screening design approach). In these designs, factors are examined at a minimum of three levels. The optimal conditions are usually derived from response surfaces build with the design results.

The optimization of a method is often divided into screening and optimization phases. During the screening phase, all factors that potentially influence the responses of interest are tested to indicate those with the largest effects. These most important factors are then further explored in the optimization phase, where their best settings, i.e., the optimum conditions, are determined. Screening and response surface designs, respectively, are applied in these steps (Massart et al., 1997).

After optimization, the method should be validated, i.e., evaluated whether it can be applied for its intended purpose (s). One of the method validation items is robustness testing, which evaluates the effects of small changes in the factors on the considered responses and which applies screening designs for this purpose (Dejaegher & Vander Heyden, 2009; Montgomery, 2005).

The classic screening and response surface designs are now presented. Some applications in electroplating processes will be further discussed in the context of process optimization.

3.1 Screening designs

Screening designs are used to indicate the most important factors from those that potentially influence the considered responses. Screening designs are applied in the context of optimizing separation techniques during screening and in robustness testing, and in the context of optimizing processes. Most often, two-level screening designs, such as fractional factorial design, are used (Montgomery, 2005), which allow the examination of a relatively large number of factors f at $L = 2$ levels in a relatively small number of experiments ($N \geq f + 1$). When f is small, two-level full factorial designs might also be applied for screening purposes (Montgomery, 2005). These designs allow the simultaneous investigation of qualitative and quantitative factors.

3.2 Two-level full factorial designs

A two-level full factorial design contains all possible combinations between the f factors and their $L = 2$ levels, leading to $N = L^f = 2^f$ experiments to be performed. Suppose that three factors, A , B , and C , each at two levels, are of interest. The design is called a 2^3 factorial design, and the eight treatment combinations are shown in Table 1. Using the “-1 and 1” notation to represent the low and high levels of the factors, we list the eight runs in the 2^3 design as in Table 1. This is sometimes called the design matrix. These designs allow the estimation of all main (i.e., of the factors) and interaction effects between the considered factors (Montgomery, 2005). The interaction effects are calculated from the columns of contrast coefficients (Table 2).

Run no.	Factors		
	A	B	C
1	-1	-1	-1
2	1	-1	-1
3	-1	1	-1
4	1	1	-1
5	-1	-1	1
6	1	-1	1
7	-1	1	1
8	1	1	1

Table 1. The 2^3 two-level full factorial design for 3 factors

3.3 Two-level fractional factorial designs

A two-level fractional factorial 2^{f-v} design contains a fraction of the full factorial design, and allows examining f factors at two levels in $N = 2^{f-v}$ runs, with $1/2^v$ representing the fraction of the full factorial ($v = 1, 2, 3, \dots$) (Table 3) (Montgomery, 2005). For fractional factorial designs, N is a power of ($N = 8, 16, 32, \dots$). Because only a fraction of a full factorial design is carried out, some information is lost.

Run no.	Contrast coefficients			
	AB	AC	BC	ABC
1	1	1	1	-1
2	-1	-1	1	1
3	-1	1	-1	1
4	1	-1	-1	-1
5	1	-1	-1	1
6	-1	1	-1	-1
7	-1	-1	1	-1
8	1	1	1	1

Table 2. The columns of contrast coefficients for the interactions

It is important to note that not all main and interaction effects can be estimated separately anymore. Some effects are confounded, meaning that they are estimated together (Table 3). For instance, in a half-fraction factorial design, each estimated effect is a confounding of two effects.

Run no.	Factors				Contrast coefficients		
	A	B	C	D	I_1	I_2	I_3
1	-1	-1	-1	-1	1	1	1
2	1	-1	-1	1	-1	-1	1
3	-1	1	-1	1	-1	1	-1
4	1	1	-1	-1	1	-1	-1
5	-1	-1	1	1	1	-1	-1
6	1	-1	1	-1	-1	1	-1
7	-1	1	1	-1	-1	-1	1
8	1	1	1	1	1	1	1

Table 3. The 2^{4-1} fractional factorial design for 4 factors, and the columns of contrast coefficients that can still be constructed. $A = BCD$, $B = ACD$, $C = ABD$, $D = ABC$, $I_1 = AB + CD$, $I_2 = AC + BD$, $I_3 = AD + BC$.

3.4 Supersaturated designs as screening designs

A saturated design is defined as a fractional factorial in which the number of factors or design variables k is given by $k = N - 1$, where N is the number of runs. Recently, considerable interest has been shown in the development and use of a supersaturated design for factor screening experiments. In this design, the number of variables k is $k > N - 1$, and these designs usually contain more variables than runs (Montgomery, 2005).

Supersaturated designs have not found popular use. They are, however, an interesting and potentially useful method for experimentation with systems that involve many variables and where only a very few of these variables are expected to produce large effects (Montgomery, 2005). Their application in the screening design for electroplating processes has not yet been reported.

3.5 Response surface designs

The most important factors—either found from screening or known from experience—are investigated in more detail using response surface designs. These, in fact, are used to determine the optimal conditions for the factors. In these designs, only quantitative and mixture-related factors are examined because the responses considered are modeled as a function of the factors. The response surfaces are then visualized. Most often, only two or three factors are further explored. For more than two factors, only fractions of the entire response surface are visualized (Massart et al., 1997; Montgomery, 2005).

Response surface methodology, by definition, is a collection of mathematical and statistical techniques that are useful for the modeling and analysis of problems in which a response of interest is influenced by many variables; the aim is to optimize this response (Montgomery, 2005). For example, suppose that a plating engineer wishes to find the levels of current density (x_1) and stirring rate (x_2) that maximize the yield (Y) of a process. The process yield is a function of the levels of current density and stirring rate, such as (Equation 1)

$$y = f(x_1, x_2) + \varepsilon \quad (1)$$

where ε represents the error observed in the response y . If we denote the expected response by (Equation 2)

$$E(y) = f(x_1, x_2) = \eta \quad (2)$$

then the surface represented by $\eta = f(x_1, x_2)$ is called a response surface.

The response surface designs can be divided into symmetrical and asymmetrical designs, depending on their appropriateness for use in an asymmetrical domain (Massart et al., 1997; Montgomery, 2005).

3.6 Symmetrical designs

Symmetrical designs cover a symmetrical experimental domain. They contain, for example, three-level full factorial and central composite designs. Often, in these designs, the central point is replicated 3–5 times, usually to estimate the experimental error. A three-level full factorial design contains all possible combinations between the f factors and their $L = 3$ levels, which leads to $N = L^f = 3^f$ runs, including one central point. Thus, for two factors, 9 runs are needed, whereas the inclusion of three factors requires 27 runs (Montgomery, 2005).

A central composite design (CCD) contains a two-level full factorial design (2^f runs), a star design (2^f experiments) and a central point, which requires $N = 2^f + 2^f + 1$ runs to investigate f factors (Massart et al., 1997; Montgomery, 2005). Thus, for two factors, 9 runs are needed, whereas for three factors, 15 are needed. The points of the full factorial design are situated at the factor levels -1 and $+1$, those of the star design are situated at the factor levels 0 , $-\alpha$ and $+\alpha$, and the central point at the factor levels is situated at 0 . Depending on the α value, two CCDs exist, i.e., a face-centered CCD (FCCD) with $|\alpha| = 1$, which examines the factors at three levels, and a circumscribed CCD (CCCD) with $|\alpha| > 1$, which examines the factors at five levels. For a so-called rotatable CCCD, the α level should be $|\alpha| = (2^f)^{1/4}$, i.e., 1.41 and 1.68 for 2 and 3 factors, respectively (Massart et al., 1997; Montgomery, 2005).

A Box-Behnken design contains $N = (2f(f - 1)) + 1$ runs, of which one is the center point (Montgomery, 2005). For two factors, no design is described. For three factors, 13 runs are described to be performed (Table 4).

Run no.	Factors		
	A	B	C
1	1	1	0
2	1	-1	0
3	-1	1	0
4	-1	-1	0
5	1	0	1
6	1	0	-1
7	-1	0	1
8	-1	0	-1
9	0	1	1
10	0	1	-1
11	0	-1	1
12	0	-1	-1
13	0	0	0

Table 4. Box-Behnken design for 3 factors

A Doehlert (uniform shell) design has equal distances between all neighboring runs (Doehlert, 1970). The Doehlert design for two factors consists of the six vertices of a hexagon with a center point, which requires $N = 7$ experiments. The design for three factors consists of a centered dodecahedron, which requires $N = 13$ runs (Table 5). Contrary to the aforementioned response surface designs, the factors are varied at different numbers of levels, e.g., one at three and one at five levels in the two-factor design, and one at three, one at five, and one at seven levels in the three-factor design.

Run no.	Factors		
	A	B	C
1	1	0	0
2	0.5	0.866	0
3	0.5	0.289	0.816
4	-1	0	0
5	-0.5	-0.866	0
6	-0.5	-0.289	-0.816
7	0.5	-0.866	0
8	0.5	-0.289	-0.816
9	0	0.577	-0.816
10	-0.5	0.866	0
11	-0.5	0.289	0.816
12	0	0.577	0.816
13	0	0	0

Table 5. Doehlert designs for three factors

3.7 Asymmetrical designs

When an asymmetrical domain should be investigated, asymmetrical designs, such as designs constructed with the uniform mapping algorithm of Kennard and Stone, can be applied (Massart et al., 1997; Kennard, 1969). These designs are called asymmetrical because when their experiments are plotted, they result in an asymmetrical shape when an asymmetrical domain is studied. These designs can also be used in a symmetrical domain, and then a symmetric shape may be obtained. Asymmetric designs are used because symmetric designs in an asymmetric domain are problematic: either they are too large and require experiments in an impossible area, or they are too small and a considerable part of the domain is not covered (Massart et al., 1997; Montgomery, 2005).

Most often, from a response surface design, the general model build for f factors is (Equation 3)

$$y = \beta_0 + \sum_{i=1}^f \beta_i x_i + \sum_{i=1}^f \beta_{ij} x_i x_j + \sum_{i=1}^f \beta_{ii} x_i^2 \quad (3)$$

where y is the response, β_0 is the intercept, β_i are the main coefficients, β_{ij} are the two-factor interaction coefficients, and β_{ii} are the quadratic coefficients. Occasionally, the interaction terms are restricted to two-factor interactions ($x_i x_j$) and the higher-order interactions are neglected, as in Equation 3. Occasionally, the non-significant terms of the model are deleted after a statistical analysis.

3.8 Data interpretation

3.8.1 Screening designs

From the results of a full factorial or fractional factorial design, the effect of each factor X on each response Y is estimated as shown in Equation 4:

$$E_X = \frac{\text{contrast}}{n2^{k-1}} \quad (4)$$

where E_x represents the effect or interaction, n is the number of replicates and k is the number of variables or factors.

Generally, a regression model estimates the relation between $N \times 1$ response vector y , and the $N \times t$ model matrix X , where N is the number of design runs, and t is the numbers of terms included in the model. The model matrix is obtained by adding a column of ones before the $t - 1$ design matrix columns, which consists of coded factor levels and the column of contrast coefficients, as defined by the experimental design (Equation 5):

$$y = (X\beta) + \varepsilon \quad (5)$$

where β is the $t \times 1$ vector regression coefficients and ε is an error vector. The regression coefficients, b , are calculated using least squares regression (Equation 6):

$$b = (X^T X)^{-1} X^T y \quad (6)$$

where \mathbf{X}^T is the transposed matrix of \mathbf{X} .

Because effects estimate the change in response when the factor levels are changed from -1 to $+1$ and the coefficients are between levels 0 and $+1$, both are related as follows (Equation 7):

$$E_X = 2b_X \quad (7)$$

Usually, a graphical and/or statistical interpretation of the estimated effects is performed to determine their significance. Graphically, normal probability or half-normal probability plots can be drawn (Montgomery, 2005). In these plots, the unimportant effects are found on a straight line through zero, whereas the important effects deviate from this line.

The statistical interpretations usually involve a calculation of a *t*-test statistic for the factors (Equation 8) and a comparison between this *t*-value and a limit value, $t_{critical}$, or between the effect E_X and a critical effect, $E_{critical}$, respectively. All effects that are greater than or equal to this $E_{critical}$ in absolute value are then considered significant (Montgomery, 2005):

$$t = \frac{|E_X|}{(SE)_e} \Leftrightarrow t_{critical} \quad (8)$$

with $(SE)_e$ being the standard error of an effect. The critical *t*-value, $t_{critical}$, depends on the number of degrees of freedom associated with $(SE)_e$ and on the significance level, usually $p = 0.05$. The critical effect, $E_{critical}$, is then obtained as follows (Equation 9):

$$E_{critical} = t_{critical}(SE)_e \Leftrightarrow |E_X| \quad (9)$$

The standard error of an effect, $(SE)_e$, can be estimated from different data: from the variance of replicated runs, from *a priori* declared negligible effects, or from *a posteriori* defined negligible effects. We consider the last two approaches the most appropriate for the proper estimation of $(SE)_e$.

3.8.2 Optimization using the desirability function

Many response surfaces imply the analysis of several responses. The simultaneous consideration of multiple responses involves first building an appropriate response surface model for each response and then attempting to find a set of operating conditions that, in some sense, optimizes all responses or at least keeps them within desired ranges. A useful approach to the optimization of multiple responses is the use of the simultaneous optimization technique popularized by Derringer and Suich (Derringer & Suich, 1980). Their procedure makes use of desirability functions. The general approach is to first convert each response Y_i , into an individual desirability function d_i that varies over the range $0 \leq d_i \leq 1$, where if response Y_i is at its goal or target, then $d_i = 1$, and if the response is outside an acceptable region, $d_i = 0$. Next, the design variables are chosen to maximize the overall desirability, $D = (d_1 \times d_2 \times \dots \times d_m)^{1/m}$, where there are m responses (Ferreira et al., 2007).

4. The main results presented in the literature concerning the use of statistic methods in electrodeposition

In the 1990s, optimization started to be essential for development of cheap and rapid process technologies. The need for more refined and functional materials, led by the electronics industry, increased the requirements for process control in electrodeposition and stimulated the use of statistical approaches for the optimization of deposition parameters. Furthermore, experimental designs had already found widespread applications in the physical sciences, mainly because of the development of sophisticated and dedicated software for statistical analyses and numerical simulations. Another factor that contributed to the increase in research using experimental design was the extensive and world-wide use of personal computers with Internet access, mainly at the end of the 1990s. Since then, the number of works found in the literature concerning experimental design, response surface methodology, and other statistical evaluations in electrodeposition processes increased considerably. These works include the evaluation of several deposition parameters in the coatings' properties and/or in their formation mechanisms. The statistical packages of well-known software and dedicated statistics programs are now used, which also enhance the presentation of the results and the response surface designs diagrams.

In the context of optimizing electrodeposition processes, the application of screening and response surface designs has already been discussed and reviewed frequently (Bezerra et al., 2008; Ferreira et al., 2004). For screening, primarily two-level full factorial (Santana et al., 2006; 2007a; 2007b; Souza e Silva et al., 2006) and fractional factorial designs (Wery et al., 1999; Hu & Bay, 2001a; 2001b; Tsay & Hu, 2002; Hu et al., 2003; Bai & Hu, 2005; Hu et al., 2006; Dubent et al., 2007) have been applied. For the actual optimization of important factors, response surface designs, such as central composite (San Martín et al., 1998; Hu & Bay, 2001a; 2001b; Tsay & Hu, 2002; Hu et al., 2003; Bai & Hu, 2005; Hu et al., 2006; Silva et al., 2008; Musa et al., 2008; Poroch-Seritana et al., 2011), Box-Behnken (Morawej et al., 2006), and Doehlert (Chalumeau et al., 2004; 2006], have been used.

4.1 Classic applications concerning the use of screening and optimization in electrodeposition

The group of Chi-Chang Hu has presented some electrodeposition experiments. To optimize the hydrogen evolution activity of Zn-Ni and Ni-P deposits, respectively, different experimental strategies, including the fractional factorial design (FFD), the path of the steepest ascent study, and the central composite design (CCD) coupled with the response surface methodology (RSM), were adopted (Hu & Bay, 2001a; 2001b; Hu et al., 2003). The same experimental strategies were used to find the optimal plating conditions in the pulse-reverse electroplating mode for non-anomalous plating of Co-Ni and Fe-Ni deposits, from chloride solutions (Bai & Hu, 2005; Tsay & Hu, 2002). The same group again reported the aforementioned strategies to study the electroplating conditions of a direct-current (DC) plating mode for the co-deposition of Sn-Zn deposits, and their composition close to the eutectic point were achieved from chloride solutions. The temperature of the plating bath, pH, and the metallic ion ratio (i.e., $\text{Sn}^{4+}/\text{Zn}^{2+}$ ratio) were found to be the key factors that affect the composition of Sn-Zn deposits in the fractional factorial design study. The effects of pH and the temperature of the plating solution on the composition of Sn-Zn deposits

were examined using a regression model in the central composite design study (Hu et al., 2006).

Concerning the electrodeposition of ternary alloys, the Prasad group has reported some studies. Ternary alloys Ni-W-B, Ni-Fe-Mo, and Ni-W-Co were electrodeposited, and operational parameters related to their corrosion resistance and deposition efficiency were optimized (Santana et al., 2006; Santana et al., 2007a; Santana et al., 2007b). The Doehlert experimental design was applied to study Au-Co electroplating optimization, and validation was performed by means of statistical analysis (Chalumeau et al., 2004; 2006). Fractional factorial design was used to analyze the influence of plating conditions on the cathode efficiency of zinc barrel electroplating and on the quality of deposited layers for low-cyanide electrolytes (Wery et al., 1999), as well as to study the determination of the suitable electroplating conditions (i.e., electrolyte composition and cathode current density) to produce 70Sn-30Zn electrodeposits (Dubent et al., 2007).

Experimental design has been applied to study the influence of several parameters on the electroplating of Cu-Zn alloy in cyanide medium (Musa et al., 2008), and response surface modeling and optimization has been used by the Senna group to study the influence of deposition parameters on the electrodeposition of both Cu-Zn and Cu-Co alloys from in citrate medium (Ferreira et al., 2007; Silva et al., 2008). Cembero & Busquets-Mataix (2009) have also used experimental design to study the most important parameters in the production of ZnO crystals by electrodeposition.

The central composite experimental design and response surface methodology have been employed for statistical modeling and analysis of results dealing with nickel electroplating process. The empirical models developed in terms of design variables (current density J (A/dm²), temperature T (°C) and pH) have been found to be statistically adequate to describe the process responses, i.e., cathode efficiency Y (%), coating thickness U (μm), brightness V (%) and hardness W (HV). The multi-response optimization of the nickel electroplating process has been performed using the desirability function approach (Poroch-Seritana et al., 2011). Ferreira et al. (2007), studying the electrodeposition process of Cu-Zn alloys from citrate bath, also used multi-response optimization and the desirability function approach to determine the best conditions (stirring speed and current density values) to deposit a Cu-Zn alloy coating with the best anticorrosive performance. Silva et al. (2007) were also able to obtain the best conditions to produce Cu-Co alloys from citrate baths, using the desirability function approach. Unfortunately, there are still few works concerning this topic in the literature.

5. Conclusions

This chapter has provided an overview of both classic and advanced experimental design setups and their data interpretation. Statistical methods, such as experimental design and response surface methodology, could be used to help the plating engineer find a better relationship among all the parameters that might simultaneously influence the properties and performance of metallic/alloy or hybrid coatings. Rather uncommon experimental setups, such as the Doehlert design as screening design, were also considered. This was followed by a discussion of the applications using fractional factorial designs as screening designs and also of the application of desirability functions to solve problems of multi-

responses. This last topic may be very useful for plating engineers to produce more adequate coatings for desired applications.

6. Acknowledgements

The authors would like to thank the Brazilian Council of Research and Development (CNPq), the Rio de Janeiro State Foundation for Research (FAPERJ), and the Rio de Janeiro State University – Prociência Program for research grants.

7. References


- Bai, A. & Hu, C. C. (2005) Composition controlling of Co-Ni and Fe-Co alloys using pulse-
Bai, A. & Hu, C. C. (2005) Composition controlling of Co-Ni and Fe-Co alloys using pulse-reverse electroplating through means of experimental strategies. *Electrochimica Acta*, Vol. 50, No. 6, (January 2005), pp. 1335-1345, ISSN: 0013-4686.
- Bezerra, M. A.; Santelli, R. E.; Oliviera, E. P.; Villar, L. S. & Escaleira, L. A. (2008) Response surface methodology (RSM) as a tool for optimization in analytical chemistry. *Talanta*, Vol. 76, No. 5 (September 2008), pp. 965-977. ISSN: 0039-9140
- Bozzini, B.; Mele, C.; D'Urzo, L.; Giovannelli, G. & Natali, S. Electrodeposition of Cu from acidic sulphate solutions in the presence of PEG: an electrochemical and spectroelectrochemical investigation – Part I. *Journal of Applied Electrochemistry*, Vol. 36, No. 1 (January 2006), pp. 87-97. ISSN: 0021-891X.
- Brankovic, S. R.; George, J.; Bae, S. -E. & Litvinova, D. (2009) Critical Parameters of Solution Design for Electrodeposition of 2.4 T CoFe Alloys. *The Electrochemical Society Transactions*, Vol. 16, No. 45, (October 2009), pp. 75-87. ISSN: 1938-5862.
- Cembrero, J. & Busquets-Mataix, D. (2009) ZnO crystals obtained by electrodeposition: Statistical analysis of most important process variables. *Thin Solid Films*, Vol. 517, No. 9, (March 2009), pp. 2859-2864. ISSN: 0040-6090.
- Chalumeau, L.; Wery, M.; Ayedi, H. F.; Chabouni, M. M. & Leclere, C. (2004) Application of a Doehlert experimental design to the optimization of an Au-Co plating electrolyte. *Journal of Applied Electrochemistry* Vol. 34, No. 11 (December 2004), pp. 1177-1184. ISSN: 0021-891X.
- Chalumeau, L.; Wery, M.; Ayedi, H. F.; Chabouni, M. M. & Leclere, C. (2006) Development of a new electroplating solution for electrodeposition of Au-Co alloys. *Surface and Coatings Technology*, Vol. 201, No. 3/4 (October 2006), pp. 1363 - 1372. ISSN: 0257-8972.
- Derringer, G. & Suich, R. (1980) Simultaneous optimization of several response variables. *Journal of Quality Technology*, Vol. 12, No. 4 (October 1980), pp. 214-219. ISSN: 0022-4065
- Dejaegher, B. & Heyden, Y. V. (2009) Sequential optimization methods. In: *Comprehensive Chemometrics*, vol. 1, S. Brown; R. Tauler & B. Walczak, (Eds.), 547-575, Elsevier, ISBN: 978-0444527035, Oxford, Great Britain.
- Drissi-Daoudi, R.; Irhzo, A. & Darchen, A. (2003) Electrochemical investigations of copper behaviour in different cupric complex solutions: Voltammetric study. *Journal of Applied Electrochemistry*, Vol. 33, No. 4 (April 2003), pp. 339-343. ISSN: 0021-891X
- Doehlert, D.H. (1970) Uniform shell designs. *The Royal Statistical Society Series C-Applied Statistics*, Vol. 19, No. 3 (March 1970), pp. 231-239. ISSN: 0035-9254.

- Düzgün, E.; Ergun, Ü.; Ercan, F.; Sert, M.; Aksu, M. L. & Atakol, O. (2010) Preparation of thin film alloys with electrodeposition from heterotrinnuclear M1–M2–M1 complexes (M1: Ni^{II}, Cu^{II}; M2: Cu^{II}, Co^{II}, Zn^{II}, Cd^{II}). *Journal of Coating Technology Research*, Vol. 7, No. 3, (May 2010), pp. 365–371. ISSN: 1547-0091.
- Dubent, S.; de Petris-Wery, M.; Saurat, M. & Ayedi, H. F. (2007) Composition control of tin–zinc electrodeposits through means of experimental strategies. *Materials Chemistry and Physics*, Vol. 104, No. 1 (July 2007), pp. 146–152. ISSN: 0254-0584.
- Ferreira, S. L. C.; dos Santos, W. N. L.; Quintella, C. M.; Neto, B. B. & Bosque-Sendra, J. M. (2004) Doehlert matrix: a chemometric tool for analytical chemistry –review. *Talanta*, Vol. 63, No. 4 (July 2004), pp. 1061–1067. ISSN: 0039-9140
- Ferreira, F. B. A.; Silva, F. L. G.; Luna, A. S.; Lago, D. C. B. & Senna, L. F. (2007) Response surface modeling and optimization to study the influence of deposition parameters on the electrodeposition of Cu–Zn alloys in citrate medium. *Journal of Applied Electrochemistry*, Vol. 37, No. 4, (April, 2007), pp. 473–481. ISSN: 0021-891X
- Finot, M. O.; Braybrook, G. D.; McDermott, M. T. (1999) Characterization of electrochemically deposited gold nanocrystals on glassy carbon electrodes. *Journal of Electroanalytical Chemistry*, Vol. 466, No. 2 (May 1999), pp. 234–241. ISSN: 1572-6657.
- Gomez, E. & Valles, E. (1999) Electrodeposition of Co plus Ni alloys on modified silicon substrates. *Journal of Applied Electrochemistry*, Vol. 29, No. 7 (July 1999), pp. 805–812. ISSN: 0021-891X
- Gupta, M. & Podlaha, E. J. (2010) Electrodeposition of CuNiW alloys: thin films, nanostructured multilayers and nanowires. *Journal of Applied Electrochemistry*, Vol. 40, No. 7 (July 2010), pp. 1429–1439. ISSN: 0021-891X
- Gurrappa, I. & Binder, L. (2008) Electrodeposition of nanostructured coatings and their characterization –a review. *Science and Technology of Advanced Materials*, Vol. 9, No. 4 (December 2008), pp. 1–11. ISSN: 1468-6996.
- Healy, J. P.; Pletcher, D. & Goodenough, M. (1992) The chemistry of the additives in an acid copper electroplating bath Part I. Polyethylene glycol and chloride ion. *Journal of Electroanalytical Chemistry*, V. 338, No. 1/2 (October 1992), pp. 155–165. ISSN: 1572-6657.
- Healy, J. P.; Pletcher, D. & Goodenough, M. (1992) The chemistry of the additives in an acid copper electroplating bath Part II. The instability of 4,5-dithiaoctane-1, & disulphonic acid in the bath on open circuit. *Journal of Electroanalytical Chemistry*, Vol. 338, No. 1/2 (October 1992), pp. 167–177. ISSN: 1572-6657.
- Hu, C. C. & Weng, C. Y. (2000) Hydrogen evolving activity on nickel-molybdenum deposits using experimental strategies. *Journal of Applied Electrochemistry*, Vol. 30, No. 4 (April 2000), pp. 499–506. ISSN: 0021-891X.
- Hu, C. C. & Bai, A. (2001) Optimization of hydrogen evolving activity on nickel-phosphorous deposits using experimental strategies. *Journal of Applied Electrochemistry*, Vol. 31, No. 5 (May 2001), pp. 565–572. ISSN: 0021-891X
- Hu, C. C. & Bai, A. (2001) Composition control of electroplated nickel-phosphorus deposits. *Surface and Coatings Technology*, Vol. 137, No. 2-3 (March 2001), pp. 181–187. ISSN: 0257-8972.
- Hu, C. C.; Tsay, C. H. & Bai, A. (2003) Optimization of the hydrogen evolution activity on zinc/nickel deposits using experimental strategies. *Electrochimica Acta*, Vol. 48, No. 7 (February 2003), pp. 907–918. ISSN: 0013-4686.

- Hu, C. C.; Wang, C. K. & Lee, G. L. (2006) Composition control of tin–zinc deposits using experimental strategies. . *Electrochimica Acta*, Vol. 51, No. 18 (May 2006), pp. 3692–3698. ISSN: 0013-4686.
- Huang, H. & Yanga, X. (2005) One-step, shape control synthesis of gold nanoparticles stabilized by 3-thiopheneacetic acid. *Colloids and Surfaces A: Physicochemistry and Engineering Aspects*, Vol. 255, No. 1/3 (March 2005), pp. 11–17. ISSN: 0927-7757.
- Illy, B.; Shollock, B. A.; MacManus-Driscoll, J. L. & Ryan, M. P. (2005) Electrochemical growth of ZnO Nanoplates. *Nanotechnology*, Vol. 16, No. 2 (January 2005), pp. 320–324. ISSN: 0957-4484.
- Jeerage, K. M. & Schwartz, D. T. (2004) Alloy Electrodeposition. *The Electrochemical Society Interface*. Vol. 16, No. 1 (January 2004), pp. 23 – 24. ISSN: 1064-8208.
- Kennard, R. W. & Stone, L. A. (1969) Computer aided design of experiments. *Technometrics*, Vol. 11, No. 1 (January 1969), pp. 137–148. ISSN: 0040-1706.
- Kharlamov, V. I.; Kruglikov, S. S.; Grigoryan, N. S. & Vagramyan, T. A. (2001) Microdistributions of electrolytic alloys and their components. *Russian Journal of Electrochemistry*, Vol. 37, No. 7 (July 2001), pp. 661–669. ISSN: 1023-1935.
- Kim, H.; Moon, J. Y. & Lee, H. S. (2009) Growth of ZnO nanorods on various substrates by electrodeposition. *Electronic Materials Letters*, Vol. 5, No. 3, (September 2009), pp. 135–138. ISSN: 1738-8090.
- Landolt, D. (1994) Electrochemical and materials science: aspects of alloy deposition. *Electrochimica Acta*, Vol. 39, No. 8/9, (June 1994), pp. 1075– 1090. ISSN: 0013-4686.
- Lu, D. L. & Tanaka, K.I. (1996) Gold Particles Deposited on Electrodes in Salt Solutions under Different Potentials. *Journal of Physical Chemistry*, Vol. 100, No. 5 (February 1996), pp. 1833–1837. ISSN: 1089-5639.
- Massart, D. L.; Vandeginste, B. G. M.; Buydens, L. M. C.; de Jong, S. P.; Lewi, J. & Smeyers-Verbeke, J. (1997) *Handbook of chemometrics and qualimetrics: Part A*, Elsevier, ISBN: 0-444-89724-0, Amsterdam, Netherlands.
- Mohanty, U. S. (2011) Electrodeposition: a versatile and inexpensive tool for the synthesis of nanoparticles, nanorods, nanowires, and nanoclusters of metals. *Journal of Applied Electrochemistry*, Vol. 41, No. 3 (March 2011), pp. 257–270. ISSN: 0021-891X
- Montgomery, D.C. (2005) *Design and analysis of experiments*, 6th edition, John Wiley, ISBN: 0-471-48735X, New York, USA.
- Morawej, N.; Ivey, D. G. & Akhlaghi, S. (2006) Improvements in the process for electrodeposition of Au-Sn alloys, *Proceedings of The International Conference on Compound Semiconductor Manufacturing Technology - CS MANTECH Conference*, pp. 201–204, Vancouver, British Columbia, Canada, April 24–27, 2006. Available from <http://www.csmantech.org/Digests/2006/index2006.html#>.
- Mosavat, S. H.; Bahrololoom, M. E. & Shariat, M.H. (2011) Electrodeposition of nanocrystalline Zn–Ni alloy from alkaline glycinate bath containing saccharin as additive. *Applied Surface Science*, vol. 257, No. 20 (August 2011), pp. 8311– 8316. ISSN: 0169-4332
- Musa, A. Y. Q.; Slaiman, J. M. A.; Kadhum, A. H. & Takriff, M. S. (2008) Effects of agitation, current density and cyanide concentration on Cu–Zn alloy electroplating. *European Journal of Scientific Research*, Vol. 22, No. 4 (October 2008), pp. 517–524. ISSN: 1450-216X.450-216X
- Nayana, K. O.; Venkatesha, T. V.; Praveen, B. M. & Bástala, K. (2011) Synergistic effect of additives on bright nanocrystalline zinc electrodeposition. *Journal of Applied Electrochemistry*, Vol. 41, No. 1 (January, 2011), pp. 39–49. ISSN: 0021-891X

- Oriňáková, R.; Turoňová, A.; Kladeková, D.; Gálová, M. & Smith, R. (2006) Recent developments in the electrodeposition of nickel and some nickel-based alloys. *Journal of Applied Electrochemistry*, Vol. 36, No. 9 (September 2006), pp. 957-972. ISSN: 0021-891X
- Poroch-Seritan, M.; Gutt, S.; Gutt, G.; Cretescu, I.; Cojocaru, C. & Severin, T. (2011) Design of experiments for statistical modeling and multi-response optimization of nickel electroplating process. *Chemical Engineering Research and Design*, Vol. 89, No. 2 (February 2011), pp. 136-147. ISSN: 0263-8762.
- Rabiot, D.; Caire, J.-P.; Nguyen, B.; Chainet, E. & Gerard, F. (1998) Optimizing an electrochemical deposition process by use of design of computer experiments. *Analisis*, Vol. 26, No. 8 (October 1998), pp. 281-284. ISSN: 0365-4877.
- Ramanauskas, R.; Gudavičiūtė, L.; Ščit, O.; Bučinskienė, D. & Juškėnas, R. (2008) Pulse plating effect on composition and corrosion properties of zinc alloy coatings. *Transactions of the Institute of Metal Finishing*, Vol. 86, No. 2, (March 2008), pp. 103-108. ISSN: 0020-2967.
- Roventi, G.; Bellezze, T. & Fratesi, R. (2006) Electrochemical study on the inhibitory effect of the underpotential deposition of zinc on Zn-Co alloy electrodeposition. *Electrochimica Acta*, Vol. 51, No. 13 (March 2006), pp. 2691-2697. ISSN: 0013-4686.
- San Martín, V. Sanllorente, S. & Palmero, S. (1998) Optimization of influent factors on nucleation process of copper in solutions containing thiourea using an experimental design. *Electrochimica Acta*, Vol. 44, No. 4 (September 1998), pp. 579-585. ISSN: 0013-4686.
- Santana, R. A. C.; Prasad, S.; Campos, A. R. N.; Araújo, F. O.; da Silva, G. P. & de Lima-Neto, P. (2006) Electrodeposition and corrosion behaviour of a Ni-W-B amorphous alloy. *Journal of Applied Electrochemistry*, Vol. 36, No. 1 (January 2006), pp. 105-113. ISSN: 0021-891X
- Santana, R. A. C.; Prasad, S.; Moura, E. S.; Campos, A. R. N.; Silva, G. P. & Lima-Neto, P. (2007) Studies on electrodeposition of corrosion resistant Ni-Fe-Mo Alloy. *Journal of Material Science*, Vol 42, No. 7 (February 2007), pp. 2290-2296. ISSN: 0022-2461.
- Santana, R. A. C.; Campos, A. R. N.; Medeiros, E. A.; Oliveira, A. L.; Silva, L. M. F. & Prasad, S. (2007) Studies on electrodeposition and corrosion behavior of a Ni-W-Co amorphous alloy. *Journal of Material Science*, Vol 42, No. 22 (July 2007), pp. 9137-9144. ISSN: 0022-2461.
- Schwarzacher, W. (2004) Kinetic roughening of electrodeposited films. *Journal of Physics: Condensed Matter*, Vol. 16, No. 26 (July 2004), pp. R859-R880. ISSN: 0953-8984.
- Schwartz, M. (1994) Deposition from aqueous solutions: an overview. In: *Handbook of Deposition Technologies for Films and Coatings - Science, Technology and Applications (2nd Edition)*, R.F. Bunshah, (Ed.), 506-616, William Andrew Publishing, London, Great Britain. ISBN: 978-0-8155-1337-7
- Senna, L. F.; Díaz, S. L. & Sathler, L. (2003) Electrodeposition of copper-zinc alloys in pyrophosphate-based electrolytes. *Journal of Applied Electrochemistry*, Vol. 33, No. 12 (December 2003), pp. 1155-1161. ISSN: 0021-891X
- Senna, L. F.; Díaz, S. L. & Sathler, L. (2005) Hardness Analysis and Morphological Characterization of Copper-Zinc Alloys Produced in Pyrophosphate-Based Electrolytes. *Materials Research*, Vol. 8, No. 3, (July 2005), pp. 275-279. ISSN: 1516-1439.
- Silva, F. L. G.; Cruz, V. G. M.; Garcia, J. R.; Luna, A. S.; Lago, D. C. B. & Senna, L. F. (2007) Estudo dos parâmetros para a produção de revestimentos de liga Cu-Co sobre

- substratos de aço ao carbono com propriedades anticorrosivas. *Proceedings of The 9th International Conference on Equipments Technology – 9th COTEQ*, pp. 1-8, Salvador, Bahia, Brazil, June 12-15, 2007. Available from CD-ROM - http://www.abende.org.br/down2/anais_2011.pdf.
- Silva, F. L. G.; Garcia, J. R.; Cruz, V. G. M.; Luna, A. S.; Lago, D. C. B. & Senna, L. F. (2008) Response surface analysis to evaluate the influence of deposition parameters on the electrodeposition of Cu-Co alloys in citrate medium. *Journal of Applied Electrochemistry*, Vol. 38, No. 12 (December 2008), pp. 1763-1769. ISSN: 0021-891X
- Skirstymonskaya, B. I. (1964) Electrodeposition of alloys. *Russian Chemical Reviews*, Vol.33 No.4, (April 1964), pp. 221-233. ISSN: 0036-021X
- Souza e Silva, P. T.; de Mello, N. T.; Duarte, M. M.; Conceição, M. M.; Montenegro, B. S. M.; Araújo, A. N.; Neto, B. B. & da Silva, V. L. (2006) Nome do artigo. *Journal of Hazard Materials B*, Vol. 128, No. 1 (January 2006), pp. 39-43. ISSN: 0304-3894.
- Takata, F. M & Sumodjo, P. T. A. (2007) Electrodeposition of magnetic CoPd thin films: Influence of plating condition. *Electrochimica Acta*, Vol. 52, No. 20 (June 2007), pp. 6089-6096. ISSN: 0013-4686.
- Tantavichet, N. & Pritzker, M. (2006) Copper electrodeposition in sulphate solutions in the presence of benzotriazole. *Journal of Applied Electrochemistry*, Vol. 36, No. 1 (January 2006), pp. 49-61. ISSN: 0021-891X
- Tsai, T. H.; Thiagarajan, S. & Chen, S. M. (2010) Green synthesized Au-Ag bimetallic nanoparticles modified electrodes for the amperometric detection of hydrogen peroxide. *Journal of Applied Electrochemistry*, Vol. 40, No. 12 (December 2010), pp. 2071-2076. ISSN: 0021-891X
- Tsay, P. & Hu, C. C. (2002) Non-anomalous codeposition of iron-nickel alloys using pulse-reverse electroplating through means of experimental strategies. *Journal of The Electrochemical Society*, Vol. 149, No. 10, (August 2002), pp. C492-C497. ISSN: 0013-4651
- Vicenzo, A.; Bonelli, S. & Cavallotti, P. L. (2010) Pulse plating of matt tin: effect on properties. *Transactions of the Institute of Metal Finishing*, Vol 88, No 5, (September 2010), pp. 248-255. ISSN: 0020-2967.
- Wery, M.; Catonné, J. C.; Ligier, V. & Pagetti, J. (1999) Zinc barrel electroplating using low cyanide electrolytes. *Journal of Applied Electrochemistry*, Vol. 29, No. 6 (June 1999), pp. 733-743. ISSN: 0021-891X
- Wua, G.; Lia, N.; Zhoua, D. & Mitsuo, K. (2004) Electrodeposited Co-Ni-Al₂O₃ composite coatings. *Surface and Coatings Technology*, Vol. 176, No. 1 (January 2004), pp. 157-164. ISSN: 0257-8972.
- Yoshida, T.; Zhang, J.; Komatsu, D.; Sawatani, S.; Minoura, H.; Pauporté, T.; Lincot, D.; Oekermann, T.; Schlettwein, D.; Tada, H.; Wöhrle, D.; Funabiki, K.; Matsui, M.; Miura, H. & Yanagi, H. (2009) Electrodeposition of Inorganic/Organic Hybrid Thin Films. *Advanced Functional Materials*, Vol. 19, No. 1 (January 2009), pp. 17-43. ISSN: 1616-3028.



Electroplating

Edited by Prof. Darwin Sebayang

ISBN 978-953-51-0471-1

Hard cover, 166 pages

Publisher InTech

Published online 11, April, 2012

Published in print edition April, 2012

This book emphasizes on new applications of electroplating with consideration for environmental aspect and experimental design. Written by experienced expert from various countries, the authors come from academia and electroplating industrial players. Here, a very detailed explanation to the new application of the electroplating is followed by a solution of the environmental issue caused by the electroplating process and concluded by experimental design for optimization of electro deposition processes.

Coverage included:

- Preparation NiO catalyst on FeCrAl Substrate Using Various Technique at Higher Oxidation Process
- Electrochemical properties of carbon- supported metal nanoparticle prepared by electroplating methods
- Fabrication of InGaN-Based Vertical Light Emitting Diodes Using Electroplating
- Integration Of Electrografted Layers for the Metallization of Deep Through Silicon Vias
- Biomass adsorbent for removal of toxic metal ions from electroplating industry wastewater
- Resistant fungal biodiversity of electroplating effluent and their metal tolerance index
- Experimental design and response surface analysis as available tools for statistical modeling and optimization of electrodeposition processes

How to reference

In order to correctly reference this scholarly work, feel free to copy and paste the following:

Lilian F. Senna and Aderval S. Luna (2012). Experimental Design and Response Surface Analysis as Available Tools for Statistical Modeling and Optimization of Electrodeposition Processes, Electroplating, Prof. Darwin Sebayang (Ed.), ISBN: 978-953-51-0471-1, InTech, Available from:

<http://www.intechopen.com/books/electroplating/experimental-design-and-response-surface-analysis-as-available-tools-for-statistical-modeling-and-op>

INTECH
open science | open minds

InTech Europe

University Campus STeP Ri
Slavka Krautzeka 83/A
51000 Rijeka, Croatia
Phone: +385 (51) 770 447

InTech China

Unit 405, Office Block, Hotel Equatorial Shanghai
No.65, Yan An Road (West), Shanghai, 200040, China
中国上海市延安西路65号上海国际贵都大饭店办公楼405单元
Phone: +86-21-62489820

www.intechopen.com

Fax: +385 (51) 686 166
www.intechopen.com

Fax: +86-21-62489821

IntechOpen

IntechOpen

© 2012 The Author(s). Licensee IntechOpen. This is an open access article distributed under the terms of the [Creative Commons Attribution 3.0 License](https://creativecommons.org/licenses/by/3.0/), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

IntechOpen

IntechOpen